



A.G.A Group
 Merton Hall Ponds
 Merton, Thetford
 Norfolk IP25 6QH
 Telephone: +44 (0) 1953 886824
 Email: info@agagroup.org.uk
 www.agagroup.co.uk

Product Specification Sheet

Firestone PondGard EDPM Rubber Liners

Synthetic rubber geomembrane liner for water containment applications.

Property	Test method	Units	Minimum Values	
			SI	Eng
Specific Gravity	ASTM D-792	gm/cc	1.2	1.2
Unit Weight	ASTM D-751	kg/m (lb/ft)	1.4	.29
Thickness, Type 1	ASTM D-412	mm (in)	1.14 +10/-20%	045 +10/-20%
Tensile Strength, Die C	ASTM D-412	MPa (psi)	9.0	1305
Ultimate Elongation, Die C	ASTM D-412	%	300	300
Tear Resistance, Die C	ASTM D-624	kN/m (lbf/in)	26.27	150
Puncture Resistance	ASTM D-4833	N (lbs)	110.8	25
Shore A Durometer	ASTM D-2240		65-10	65-10
Resistance to Ozone 7 days/100 @ 37.8° C (150° F) 50% ext.	ASTM D-1149		No Cracks	No Cracks
Multiaxial Elongation	ASTM D-5617	%	100	100
Oven Aging At 116° C (240° F) for 670 hours	ASTM D-573			
Tensile strength Die C	ASTM D-412	MPa (psi)	8.3	1205
Ultimate elongation, Die C	ASTM D-412	%	200	200
Tear Resistance, Die C	ASTM D-624	kN/m (lbf/in)	21.9	125
Xenon Arc for 5040 kJ/(m ² .nm) @ 340 nm @ 80°C	ASTM G-155/G-151			
Visual Inspection- 7X No cracks or crazing bent loop @10% strain	ASTM D-518		Pass	Pass
Brittleness Point	ASTM D-2137		-45°C	-49°F
Water Resistance weight after immersion 166 hrs @ 70° C (158° F)	ASTM D-471	%	+8,-2	+8,-2
Water Vapor Permeability (max.)	ASTM E-96	Perm-mils	2.0	2.0
Linear Dimensional Change,max	ASTM D-1204	%	+/- 1.0	+/- 1.0
Chronic Toxicity Screening	EPA/600/4-89/ 001 ASTM E-729	Method 1000.0	passes passes	passes passes

The A.G.A. Group provided this information for reference purposes only. This specification is not intended as a warranty or guarantee. The company assumes no liability in connection with the use of this information.

Please contact us for current specifications and changes arising from new developments.

