



Product Specification Sheet

A.G.A. 125 Coir Blanket

Long Term Erosion Control Blanket

AGA 125 Coir Blanket has a functional longevity of approximately 36 months (NOTE: functional longevity may vary depending upon climatic conditions, soil, geographic location, and elevation).

AGA 125 Coir Blanket

Typical applications

Medium/long term erosion control applications on steep slopes where vegetation is the primary stabilising medium.

Product materials

Matrix 100% Coconut fibre (0.50 lb. /yd² [0.27 kg/m²])
 Netting both sides heavyweight UV stabilised (3.0 lbs. /1,000 ft² [1.47 kg/100 m²] approximate weight)
 Thread 100% Black Polypropylene

Product construction

100% coconut fibre blanket of consistent thickness covered on the top and bottom with heavyweight polypropylene netting having ultraviolet additives to delay breakdown and approximate 0.625 x 0.625 inch (1.59 x 1.59 cm) mesh size. The blanket shall be sewn together on 1.50 inch (3.81 cm) centres with UV stable polypropylene thread.

Material Content

Property	Test Method	Typical
Thickness	ASTM D5199/ECTC	0.35 in (8.91 mm)
Resiliency	ECTC Guidelines	82%
Mass per Unit Area	ASTM D6475	8.00 oz/yd ² (271 g/m ²)
Water Absorption	ASTM D1117/ECTC	110%
Swell	ECTC Guidelines	13.00%
Stiffness/Flexibility	ASTM D1388/ECTC	0.75 oz-in (8,368 mg-cm)
Light Penetration	ECTC Guidelines	16.70%
MD Tensile Strength	ASTM D5035	3.12 kN/m
MD Elongation	ASTM D5035	13.60%
XD Tensile Strength	ASTM D5035	3.05 kN/m
XD Elongation	ASTM D5035	25.50%

The A.G.A. Group provided this information for reference purposes only. This specification is not intended as a warranty or guarantee.

The company assumes no liability in connection with the use of this information.

Please contact us for current specifications and changes arising from new developments.

11/09

